

DECOFOND

DECOFOND is a premixed lime mortar specially designed as a base coat for irregular, or heterogeneous, interior walls. It may also be used as a smooth finish coat on interior or exterior walls.

PACKAGING

- 15 kg (33 lbs) pail
- 30 kg (66 lbs) bag

WALL PREPARATION

- Application without fiberglass mesh: Bricks, concrete blocks, and drywall.
- Application with fiberglass mesh: Wall with dissimilar materials, old gypsum based materials, adobe, pise, and cob.

MIXING

- Mechanically mix approximately 3/4 to 1 gallon (3 to 3.5 liters) of clean water in a 33 lbs. (15 kg) pail of DECOFOND.
- The mix shall be homogeneous, without lumps or unmixed material.
- Working time is 15 to 45 minutes, depending on environmental conditions.

CONSUMPTION

- One pail will cover 120 square feet at 1/32", 60 square feet at 1/16" thickness or 30 square feet at 1/8" thickness (2 passes).
- One bag will cover 240 square feet at 1/32", 120 square feet at 1/16" thickness or 60 square feet at 1/8" thickness (2 passes).

APPLICATION WITHOUT MESH

- Apply in one to two passes, 1/32" to 1/8" (1 to 4 mm). The total maximum thickness may not exceed 3/8" (10 mm) in the deepest depressions.

APPLICATION WITH MESH

- Embed the mesh in a 1/8" to 1/4" coat of DECOFOND. The mesh should extend a minimum of 6" (150 mm) on each side of the joint.
- Apply a second coat, 1/16" to 1/8" (2 to 4 mm), in one pass to level the surface.
- A fine sponge float finish is recommended when DECOFOND is used as a base coat for DECOLISS
- A sponge float may be used prior to steel troweling or polishing when using DECOFOND as a finish coat.

SUGGESTED FINISHES OVER DECOFOND

- Lime Paint
- DECOLISS