

# Lime Concrete Flooring

## Lime Concrete Compressive Strength

The following details are given for information purposes only. Final dosages and application should be checked with our technicians

### Lime Concrete Compressive Strength

|          | PSI   | MPa  |
|----------|-------|------|
| 7 days   | 725   | 5    |
| 28 days  | 1,015 | 7    |
| 60 days  | 1,595 | 11   |
| 90 days  | 2,000 | 13.8 |
| 4 months | 2,276 | 15.7 |
| 5 months | 2,436 | 16.8 |
| 6 months | 2,465 | 17   |