

Lime Concrete Flooring

Lime Concrete Compressive Strength

The following details are given for information purposes only. Final dosages and application should be checked with our technicians

Lime Concrete Compressive Strength

	PSI	MPa
7 days	725	5
28 days	1,015	7
60 days	1,595	11
90 days	2,000	13.8
4 months	2,276	15.7
5 months	2,436	16.8
6 months	2,465	17