

### ANNEX 3

#### St. Astier natural hydraulic limes (NHL): hydraulicity and properties

Hydraulicity: % of soluble silica and relative hydraulic properties

| EU NORM (prov) 459-1 | NHL Classification |  |
|----------------------|--------------------|--|
| NHL 5                | 5-15               |  |
| NHL 3.5              | 3.5-10             | Psi (N/mm2) @ 28 days (mortars prepared with a binder:sand ratio of 1:1) |
| NHL 2                | 2-7                |  |

